

**Product Data Sheet****EASTMAN Chlorinated Polyolefin 343-3****(50% Solids in Xylene)**

Property ^a	Typical Value, Units ^c
Specific Gravity @ 25°C/25°C	0.986
Flash Point Tag Closed Cup	27°C (80°F)
Color, Gardner	11
Chlorine	26-32 wt %
Specific Gravity, Solid CPO @ 25°C/25°C	1.108

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^cUnits are in SI or US customary units.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

List of Applications

- Adhesion promoter for inks
- Adhesion promoter for paints
- Coatings
- Printing inks
- Coatings for plastic

Eastman Chemical Company and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.