



## Product Data Sheet

### **Eastman Chlorinated Polyolefin 153-2 (25% Solids in Xylene)**

#### **Application/Uses**

- Additive for paint
- Automotive OEM
- Coatings for Automotive Plastics
- Coatings for plastic
- Coatings
- Laminating
- Printing Inks
- Truck/Bus/Commercial Vehicles

#### **Product Description**

Eastman Chlorinated Polyolefin 153-2 is a 25% solution of a chlorinated polyolefin in xylene. It is 21-25 wt. % chlorine and has a Gardner color value of 12-15. Chlorinated Polyolefin 153-2 has excellent heat stability at temperatures greater than those normally encountered under actual use conditions.

#### **Typical Properties**

<b>Property</b>	<b>Typical Value, Units</b>
Form	25% in Xylene
Color, Gardner	12-15
Specific Gravity @ 25°C/25°C	0.97
Flash Point Tag Closed Cup	27°C (81°F)
Fire Point	30°C (86°F)
Chlorine	21-25 wt %
Specific Gravity, Solid CPO @ 25°C/25°C	1.105

#### **Comments**

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*