

Levelling agent for coil coatings and other solvent-based and solvent-free coatings.

Composition:	Acrylic copolymer			
Data:	Active ingredients	:	69 - 71%	
	Solvent	: alkyl benzene with high boiling point (185-209 °C)		
	Density at 20 °C	:	0.98 - 1.00 g/cm ³	DIN 51757
	Flashpoint	:	49 °C	ISO 3679
	Colour	:	max. 3	ISO 4630
	Appearance	:	clear to slightly hazy, colourless liquid	
Addition:	0.5 - 2.0% on total formulation			
Properties:	EFKA- 3778:			
	 improves levelling prevents cratering helps substrate wetting does not interfere with intercoat adhesion 			
Application:	EFKA- 3778 is especially suitable for: • coil coatings • polyurethane coatings • stoving enamels • two-pack epoxy compounds • air-dried alkyd systems			
Incorporation:	EFKA- 3778 should be added at the end of the batch preparation.			
Storage:	EFKA- 3778 should be stored in a cool dry place and will keep up to one year after delivery date in original unopened container.			
Packaging:	25 kg and 190 kg non-returnable containers.			