



Desmophen[®] A 265 BA

Type	Hydroxyl-bearing polyacrylate
Form supplied	approx. 65 % in butyl acetate
Uses	As a co-reactant, primarily with Desmodur [®] N 75 or N 3390, in the formulation of two-component polyurethane coatings with good gloss retention, lightfastness and resistance to chalking.

Specification Property	Value	Unit of measurement	Method
Hazen color value	≤ 150		DIN EN 1557
Acid value	≤ 15	mg KOH/g	DIN EN ISO 2114
Viscosity at 23 °C	2300 ± 500	mPa·s	DIN EN ISO 3219/A.3
Non-volatile content (1 g resin/1 h at 125 °C, convection oven)	65 ± 1	%	DIN EN ISO 3251
Hydroxyl content	2.0 ± 0.3	%	DIN 53 240/2
Water content	≤ 0.1	%	DIN 51 777/1

Other data* Property	Value	Unit of measurement	Method
Equivalent weight	approx. 850		
Density at 20 °C	approx. 1.06	g/ml	DIN EN ISO 2811-2
Flash point	approx. 25	°C	DIN EN ISO 1523

*These values provide general information.



Desmophen[®] A 265 BA

Solubility / thinnability

Desmophen A 265 BA can be thinned to a resin content of 30 % using ketones, esters, ether esters, toluene, xylene and solvent naphtha[®] 100. However, the solutions formed must be tested for their storage stability. It is not compatible with aliphatic hydrocarbons. Only PU grade solvents should be used (< 0.05 % water). They should contain no other reactive impurities.

Compatibility

Generally speaking, Desmophen A 265 BA is miscible with the Desmodur and Desmophen products listed. However, the combinations must be tested for their compatibility. Desmophen A 265 BA can be mixed with Desmodur N 75, N 3390, Z 4470 and L, with Desmophen 670, 680 and 690, and with most Desmophen A products. It is also compatible with low-viscosity nitrocellulose chips and certain vinyl copolymers. Nevertheless, compatibility testing is always advisable.

Properties / Applications

Desmophen A 265 BA is used primarily in combination with Desmodur N 75 or N 3390 to formulate automotive coatings. The cured paint films are hard but flexible. They have high gloss, high body and good lightfastness and weather stability. Desmophen A 265 BA can be pigmented easily. If using organic pigments, nitrocellulose chips have proved ideal as the paste binder.

Storage

When stored in sealed containers at temperatures not exceeding 30 °C, the product will remain stable for at least 6 months.

Safety

Hazards identification

Flammable. Repeated exposure may cause skin dryness or cracking. Vapours may cause drowsiness and dizziness. The safety data sheet (030949) should be observed. This contains information on labeling, transport and storage as well as on handling, product safety and ecology.

This Information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery. This does not apply to Trial-Products.

Editor: Coatings, Adhesives & Sealants
Bayer MaterialScience AG,
D-51368 Leverkusen, Germany
www.bayercoatings.com

Contact:
Ackermann, Petra
Tel. +49 214 / 30-56465