

Setalux 1152 SS-60 Acrylic Polyol

NV ¹	% 61
Solvent.....	Xylene/Methoxy propyl acetate
Viscosity (23°C, Pa.s).....	3.50
Colour (max. value).....	≤ 75 APHA
OH - % (on solids).....	4.2
HEW ²	660
Density (kg/dm ³).....	1.04
Acid value: (mg KOH/gr).....	5.06
Appearance: Clear and free of extraneous matter	

Recommended proportion with Desmodur Poly isocyanate Resin

Type of Desmodur	Proportion PHR**
Desmodur N75 MPA/X	39
Desmodur N 3390 BA/SN	32.5
Desmodur Z4470 BA	53.5
Desmodur BL 3175 SN	57.3

** parts w per 100 parts w of Setalux 1152 SS-61

Remarks : Setalux 1152 SS61 is a standard Acrylic Polyol Resin, highly recommended for good appearance & gloss , chemical resistance , drying Speed , high hardness and recommended for durability.

Application: Clear Coat and solid colour topcoat for agricultural, construction and earthmoving equipment, Industrial Metal, Marine and Protective Coatings.

1: Suitable for VOC compliant coatings according to Directive 2004/42/CE of the European community.

2:Hydroxy Equivalent Weight, calculated on delivery form.