

ZINC PHOSPHATE PZ20

ZINC PHOSPHATE TETRAHYDRATE, $\text{Zn}_3(\text{PO}_4)_2 \cdot 4\text{H}_2\text{O}$

ZINC PHOSPHATE

PZ20 0423G

DESCRIPTION

Zinc phosphate PZ20 is a corrosion inhibiting pigment suitable for a wide range of applications, from DIY to more demanding ones such as coil coatings. It is a stable and non-hygroscopic white powder with a low tinting strength, it is easily dispersed. Thanks to its low solubility, Zinc phosphate PZ20 is compatible with a wide range of solvent and water based resins.

Technical data

	Nominal value	Tolerance (+/-)	
Zn content (%) - on the ignited product	50.0	2.0	ICP
PO ₄ content (%) - on the ignited product	48.0	2.0	ICP
Oil absorption (cm ³ /100 g)	27	5	ISO 787-5
Sieve residue - 45 µm (%)	0.05	max	ISO 787-7
pH	6.5	1.0	ISO 787-9
Pb Content (ppm)	90	max	ICP
Cd Content (ppm)	100	max	ICP
Density (g/mL)	Typ. 3.2		ISO 8130-2
D50 (µm)	Typ. 7		ISO 13320
Fineness	North	Typ. 7	ISO 787-5
	Hegman	Typ. 5.5	ISO 1524
Bonded water content (%) - 1h at 600°C	Typ. 15.7		Gravimetry

Recommended shelf life: 5 years

Formulators Guidelines

Solvent Based

	Performance
Short oil alkyd	★ ★ ★
Medium/long oil alkyd	★ ★
High solid epoxy	★ ★
2K epoxy	★ ★
Epoxy ester	★ ★
PU	★ ★

Specialty coatings

Wash primer	★
Coil coating	★ ★ ★*
Powder coating	

Water Based

	Performance
Water reducible alkyd	★ ★
Alkyd emulsion	★ ★
Epoxy ester	★ ★
2K epoxy	★ ★
Acrylics/modified acrylics	★ ★

Excellent: ★ ★ ★ Good: ★ ★ Possible: ★
Not yet tested: ____ Not recommended: nr
*: Normally used in association with other pigments (ex: ion exchanged Silica)

Best performances are obtained with a typical loading of 5 to 12% by weight on the total formulation and a PVC ranging from 20% to 40 %

SNCZ
L'ANTICORROSION

45/49, Chaussée Jules César
F-95250 BEAUCHAMP
✉ tech.support@sncz.net
☎ +33 1 30 40 57 57
WWW.SNCZ.COM

The information presented herein is true and accurate to the best of our knowledge, but without any guarantee unless explicitly given. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestion.