

Full shade

Standard depth of shade 1/3



Sicomin Yellow FC 1922



Sicomin Yellow FC 2022



Sicomin Red FC 3022



Sicomin Red FC 3025



Sicomin Red FC 3125

DELETED

DELETED

Sicomin Red FC 3130 S

Colour Index	Fastness to weathering	Fastness to light	Reduction ratio at 1/3 ST	Heat stability °C	Overspray fastness	Fastness to acids	Fastness to alkalis
34 77603	Pur 3-4 1/3 ST 3-4 1/25 ST 3-4	Pur 6-7 1/3 ST 7 1/25 ST 7	1,3	180	5	3	3
34/104 77603 77605	Pur 3-4 1/3 ST 3-4 1/25 ST 3-4	Pur 6-7 1/3 ST 7 1/25 ST 7	1,3	180	5	3	3
104 77605	Pur 3-4 1/3 ST 3-4 1/25 ST 3-4	Pur 5 1/3 ST 6 1/25 ST 7	1,1	180	5	2	2
104 77605	Pur 4-5 1/3 ST 4-5 1/25 ST 4-5	Pur 7 1/3 ST 8 1/25 ST 8	1,2	180	5	3	3
104 77605	Pur 4-5 1/3 ST 4-5 1/25 ST 4-5	Pur 7 1/3 ST 8 1/25 ST 8	0,7	180	5	3	3
104 77605	Pur 4-5 1/3 ST 4-5 1/25 ST 4-5	Pur 7-8 1/3 ST 8 1/25 ST 8	0,6	180	5	4	4