

Standardfarbtiefe 1/3
Standard depth of shade 1/3
Intensité de coloration standard 1/3
Intensidad standard 1/3



Standardfarbtiefe 1/25
Standard depth of shade 1/25
Intensité de coloration standard 1/25
Intensidad standard 1/25

Heliogen Blau L 6700 F
Heliogen Blue L 6700 F
Bleu Heliogen L 6700 F
Azul Heliogen L 6700 F

100

Heliogen Blau L 6875 F
Heliogen Blue L 6875 F
Bleu Heliogen L 6875 F
Azul Heliogen L 6875 F

100



Heliogen Blau L 6900
Heliogen Blue L 6900
Bleu Heliogen L 6900
Azul Heliogen L 6900

100



Heliogen Blau L 6901 F
Heliogen Blue L 6901 F
Bleu Heliogen L 6901 F
Azul Heliogen L 6901 F

100



Heliogen Blau L 6920
Heliogen Blue L 6920
Bleu Heliogen L 6920
Azul Heliogen L 6920

Colour Index	Wetterechtheit Fastness to weathering Solidité aux intempéries	Lichtechtheit Fastness to light Solidité à la lumière	Autfallverarbeitbarkeit Rapport ratio (AV) $\frac{1}{3}$ Relación d'elaboración $\frac{1}{3}$	Temperaturbeständigkeit $\text{p. } \frac{1}{3}$ Heat stability $\text{p. } \frac{1}{3}$ ST Estabilidad térmica °C	Überlackierbarkeit °C Overspray fastness Solidité au réchappissage	Säurefestigkeit Fastness to acids Solidité aux acides	Alkaliefestheit Fastness to alkalis Solidité a los alcalis
15:6 74160	Pur $5-$ $\frac{1}{3}$ ST $5-$	Pur 8 $\frac{1}{3}$ ST 8	11,9 $\frac{1}{25}$ ST 8	> 200	5	5	5
15:2 74160	Pur $5-$ $\frac{1}{3}$ ST $5-$	Pur 8 $\frac{1}{3}$ ST 8	13,3 $\frac{1}{25}$ ST 8	> 200	5	5	5
15:1 74160	Pur $5-$ $\frac{1}{3}$ ST $5-$	Pur 8 $\frac{1}{3}$ ST 8	11,5 $\frac{1}{25}$ ST 8	> 200	5	5	5
15:2 74160	Pur $5-$ $\frac{1}{3}$ ST $5-$	Pur 8 $\frac{1}{3}$ ST 8	10,1 $\frac{1}{25}$ ST 8	> 200	5	5	5
15:1 74160	Pur $5-$ $\frac{1}{3}$ ST $5-$	Pur 8 $\frac{1}{3}$ ST 8	12,7 $\frac{1}{25}$ ST 8	> 200	5	5	5